

WAX RECOMMENDATION **TOKO**[®]

Sisu Ski Fest

ABR Ski Trails to downtown Ironwood, MI

Saturday, January 9

10 A.M. CST 42K Wave starts

11 A.M. CST 21K Wave starts

Freestyle and Classic divisions

Forecast/Conditions: Mostly cloudy overnight with a low around -8 rising to -2F at 10 A.M. and 2F at 11 A.M. Finishing time temperature between 9-13F. New snow in days leading up to event should be machine worked and packed. Expect medium-firm track depending on grooming plan. No snow expected during event.

Glidewax: Due to the extreme cold, the base needs extra hardness. Apply LF Blue, scrape and brush, then apply LF Blue/LF Moly mixed 1:1, scrape and brush. Then apply HF Blue, sprinkle on Nordlite Powder X-cold, iron in together, scrape and brush. Finish by rotocorking JetStream Blue, brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: Roughen base with 150 grit sandpaper, iron in Carbon BaseWax Green, cork smooth, let cool. Then apply 2 layers of Carbon GripWax Blue, corking between layers. 42K racers cover with 3 layers of Carbon White, and 21K racers cover with 1 layer of Carbon White.

Structure: A fine linear structure will best suit these conditions. No additional structure should be added using the Toko Structurite tool.

Check the WaxTip page at www.TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or System 3 wax of the same color (Yellow, Red or Blue). For those who do not have a rotocork for applying JetStream, the next best thing is to iron it in.

Racing - Service