

WAX RECOMMENDATION TOKO®

Re-Mastered

Ponderosa State Park, McCall, ID

Saturday, January 20

10 A.M.

14K/28K/42K, Skate

Mass start

6K laps

<https://www.mccallnordic.com/racing/remastered/>

Forecast/Conditions: Several inches of new snow midweek with significant warming toward the end of the week. Friday night forecasted low of 33, start temperature of 34 with a high of 38. Rain and/or snow mix Friday through Saturday. Expect the course to become soft with skier traffic.

Glidewax: Apply High Performance Blue Hot Wax, scrape and brush. Sprinkle on HP Powder Red, iron in, let cool, scrape and brush. If you do not have HP Powder, apply BP Blue Hot Wax, scrape and brush, then apply HP Red Hot Wax, scrape and brush.

Prior to the start, if snow is wet cover with High Performance Liquid Paraffin Yellow, let dry for 10 minutes then polish with the Polishing Brush Liquid Paraffin.

Structure: A universal structure covered by one pass with the Red Structurite tool after scraping and brushing the final Hot Wax. If snow is wet, substitute with the Yellow Structurite tool (prior to spraying HP LP Yellow).

Created by Randy Anderson, Toko Tech Team member since 2015. Highbasin@gmail.com

Check the [Wax Tips](#) page at [TokoUS.com](#) before all of your races for the latest waxing information. Toko Race Wax Tips offer racers precise waxing advice on how to make skis perform optimally for a given event. If you do not have High Performance wax, substitute Performance or Base Performance wax of the same color (Yellow, Red or Blue), as the temperature ranges are the same. All Race Wax Tips recommend ONLY fluorine-free products. Older HP or P Toko waxes (Liquid or Hot Wax) contain fluorine. New labels look very similar but all say PFC Free. To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at [TokoUS.com](#).

Racing - Service