

# WAX RECOMMENDATION



## ARIENS U.S. BIATHLON MASTER NATIONALS

Ariens Nordic Center, Brillion, WI – Friday, Feb 13

3 P.M. Zero, 5 P.M. Race, multiple distances 4.5k to 7.5k, Skate

Interval starts, multi-lap

<https://ariensnordic.com/calendar/u-s-biathlon-masters-nationals-ariens-biathlon-festival/>

---

**Forecast/Conditions:** Thursday night low is expected to be in the mid-20s. Expect a firm skate deck of well machined, mostly manmade snow that will glaze and break down with heavy skier traffic. Races are during the peak afternoon temperatures and sun. Expect the temperature to be around 40 during the races with partly sunny skies.

**Glidewax:** Apply HP Yellow Hot Wax, scrape and brush, sprinkle on [Jet Powder](#) Yellow, make two passes with iron at 180c, let cool, scrape and brush using the copper brush and polish with a merino wool roller. Then quickly (about 3 to 4 seconds) spray [Jet Liquid](#) Yellow tail to tip, let sit for 10 minutes, go ski.

**Gripwax:** N/A

**Structure:** A wet structure covered by one pass with the Yellow Structurite tool after scraping and brushing the final Hot Wax or polishing the Jet Powder but before applying Jet Liquid will best suit these conditions.

*Created by Ben Lund, Toko Tech Team member since 2000*

**Racing-Service**

Check the [Wax Tips](#) page at [TokoUS.com](http://TokoUS.com) before all of your races for the latest waxing information. Toko Race Wax Tips offer racers precise waxing advice on how to make skis perform optimally for a given event. If you do not have High Performance wax, substitute Performance or Base Performance wax of the same color (Blue, Red or Yellow), as the temperature ranges are the same. For a more economical option, omit Jet topcoats. All Race Wax Tips recommend ONLY fluorine-free products. To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.