

WAX RECOMMENDATION



WISCONSIN STATE HS DISTANCE CHAMPIONSHIP

Birkie Trailhead, Cable, WI – Sunday, Feb 8

9 A.M., 6.2k/3.1k, Freestyle

Pursuit start on a 3.1k lap course. Note various start times

<https://www.wisconsinxcski.org/state-meet/>

Forecast/Conditions: Overnight low of about 8F, start time temperature will be around 20, high around 30. Mostly cloudy with a gentle breeze. Expect glazed and machined track conditions.

Glidewax: **Morning:** Apply HP Blue Hot Wax/HP Red Hot Wax mixed 1:1, scrape and brush, lightly rub on Jet Bloc Red, polish with the Rotary Brush Merino Wool, repeat the Jet Bloc rub/polish for a second coat. Then quickly (about 2 to 3 seconds) spray [Jet Liquid](#) Red tail to tip, let sit for 10 minutes, go ski.

Afternoon: Apply HP Red Hot Wax, scrape and brush, lightly rub on Jet Bloc Red, polish with the Rotary Brush Merino Wool, repeat the Jet Bloc rub/polish for a second coat. Then quickly (about 2 to 3 seconds) spray [Jet Liquid](#) Red tail to tip, let sit for 10 minutes, go ski.

Gripwax: N/A

Structure: A fine structure covered by one pass with the Red Structurite tool after scraping and brushing the final Hot Wax or polishing the Jet Bloc but before applying Jet Liquid will best suit these conditions.

Created by Frank Lundein, Toko Tech Team member since 1999

Racing-Service

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. Toko Race Wax Tips offer racers precise waxing advice on how to make skis perform optimally for a given event. If you do not have High Performance wax, substitute Performance or Base Performance wax of the same color (Blue, Red or Yellow), as the temperature ranges are the same. For a more economical option, omit Jet topcoats. All Race Wax Tips recommend ONLY fluorine-free products. To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.