

WAX RECOMMENDATION



Tannenbaum Classic

Tamarack Lodge XC, Mammoth Lakes, CA

Sunday, December 11

10 A.M.

10K/5K; Juniors 3K/1K

Wave start, Diagonal Stride Only

1-2laps per 5K

<http://tamaracklodge.com>

Forecast/Conditions: Overnight low 27, temperature at start 30, high of 35. New snow leading in to the race should make for good classic skiing. Snow showers likely on race day. Windy.

Glidewax: Apply LF Black, scrape and brush, then apply HF Red, scrape and brush. Finish by crayoning JetStream Red, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: Roughen base with 150 grit sandpaper, iron in Nordic Base Wax Green, cork smooth, let cool. Then apply 3-5 layers of Nordic GripWax Red, corking between layers.

Structure: A fine linear structure covered by one pass with the Blue Structurite tool (before JetStream application) will best suit these conditions.

Created by Ben Grasseschi, Toko Tech Team member since 2005.

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at TokoUS.com.

Racing - Service