

WAX RECOMMENDATION



AMH Anchorage Cup Sprint Relay

Kincaid Park, Anchorage, AK

Sunday, December 11

Noon

2 skiers x 2 laps x 1K, Skate

Three mass starts from the stadium based on category

1K lap

More info [here](#)

Forecast/Conditions: There is a chance of snow this week before the race. Saturday night mostly clear, low zero F to 10 above. Sunday high 5F-15F. Recent new snow mixed with manmade snow.

Glidewax: Apply LF Blue, scrape and brush, then apply HF Blue, scrape and brush. Finish by crayoning JetStream Blue, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: N/A

Structure: A universal grind covered by one pass with the Blue Structurite tool before JetStream application will best suit these conditions.

Created by Patrick McGownd, Toko Tech Team member since 2000.

Check the [Wax Tips](#) page at [TokoUS.com](#) before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at [TokoUS.com](#).

Racing - Service