

WAX RECOMMENDATION



Book Across The Bay

Maslowski Beach, Ashland, WI

Saturday, February 18

6 P.M.

10K, Skate and Classic

Wave start

Point to Point race

Forecast/Conditions: Overnight low 32, temperature at start will be 40. No new snow with partly cloudy skies. Expect very icy transformed snow with high moisture.

Glidewax: Apply LF Black, scrape and brush, then apply HF Blue/HF Yellow mixed 1/1, scrape and brush. Finish by crayoning JetStream Yellow, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: Roughen base with 150 grit sandpaper, apply a thin layer of Base Klister Green, heat, smooth, let cool. Then apply a thin layer of Nordic Klister Yellow, heat, smooth. Consider a mechanical structure ski if possible. If using skin skis, see our [skin treatment options](#) for best results.

Structure: A universal grind covered by one pass with the Yellow Structurite tool (before JetStream application) will best suit these conditions.

Racing - Service

Created by Blaise Sopiwnik, Toko Tech Team member since 2014.

Check the [Wax Tips](#) page at [TokoUS.com](#) before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at [TokoUS.com](#).