

# WAX RECOMMENDATION

# TOKO<sup>®</sup>

## Minnesota Finlandia

Buena Vista Ski Trail, Bemidji, MN

Saturday, February 18

10 A.M. 25K Classic

10:30 A.M. 50K/25K Freestyle

<http://www.minnesotafinlandia.com/>

**Forecast/Conditions:** Friday's afternoon high around 46 with mostly sunny skies. Friday night's low around 29. Temperature at the start of the races expected in the upper 30s with mostly sunny skies, rising into the mid-40s in the early afternoon. Watch for possible course modifications because of high temperatures.

**Glidewax:** Apply LF Black, scrape and brush, then apply HF Black/HF Yellow mixed 1:1, scrape and brush. Finish by crayoning JetStream Yellow, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

**Gripwax:** Roughen base with 150 grit sandpaper, heat in Nordic Base Klister Green, smooth, let cool. Then heat in a smooth layer of Nordic Klister Yellow, smooth, let cool. If using skin skis, see our [skin treatment options](#) for best results.

**Structure:** A universal grind covered by one pass with the Yellow Structurite tool (before JetStream application) will best suit these conditions.

Created by Mike Lundeen, Toko Tech Team member since 2004.

Check the [Wax Tips](#) page at [TokoUS.com](http://TokoUS.com) before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at [TokoUS.com](http://TokoUS.com).

# Racing - Service