

WAX RECOMMENDATION



Wisconsin Nordic Ski League Championship

Birkie Trailhead, Cable, WI

Saturday, February 11

9:30 A.M. Boys HS, 11:15 A.M. Girls HS

1 P.M. MS Boys, 1:30 P.M. Girls MS

5K/2.5K Skate, Interval start

HS 2 laps and MS 1 lap

<http://www.winordicski.org>

Forecast/Conditions: Friday night mostly cloudy with a low around 26 and west wind around 5 mph. Saturday mostly cloudy, with race time temperature 23 to 33.

Glidewax: Apply LF Black, scrape and brush, then apply HF Red, scrape and brush. Finish by crayoning JetStream Red, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad. Middle School race replace HF Red with HF Blue/HF Yellow mixed 1:1 and finish by spraying an even layer of HelX 2.0 Yellow, let dry and ski. Do not brush or polish.

Structure: A universal grind covered by one pass with the Red Structurite tool before JetStream application will best suit these conditions.

Created by Michael Young, Toko Tech Team member since 2005.

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at TokoUS.com.

Racing - Service