

WAX RECOMMENDATION



Great Lakes Super Bowl JNQ #5

Al Quaal Recreation Area, Ishpeming, MI

Saturday, February 4

1 P.M.

5K Skate

Interval start

<http://www.superiortiming.com/registration>

Forecast/Conditions: Friday night mostly cloudy, with a low around 4F. Saturday a 50 percent chance of snow after 1 PM. Partly sunny, with race temperature steady near 20 and a 60 percent to 70 percent relative humidity. Expect machine worked and packed powder.

Glidewax: Apply LF Black, scrape and brush, then apply HF Blue/HF Red mixed 1/1, scrape and brush. Finish by crayoning JetStream Blue, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: N/A

Structure: A fine linear structure covered by one pass with the Blue Structurite tool (before JetStream application) will best suit these conditions.

Created by Michael Young, Toko Tech Team member since 2005.

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at TokoUS.com.

Racing - Service