

# WAX RECOMMENDATION



## Mammoth Marathon

Tamarack Lodge XC, Mammoth Lakes, CA

Sunday, April 2

8:30 A.M.

42K/21K; Juniors 10K/3K/1.5K

Wave start

Multiple loops

<http://tamaracklodge.com>

**Forecast/Conditions:** Overnight low 24, temperature at start 30, high of 53. New snow possible on Thursday but snow should be transformed and slightly dirty on race day. Sunny, light winds.

**Glidewax:** Apply LF Black, scrape and brush, then apply HF Red/HF Yellow mixed 1:1, scrape and brush. Finish by crayoning JetStream Yellow, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

**Gripwax:** N/A

**Structure:** A warm structure covered by two passes with the Yellow Structurite tool (before JetStream application) will best suit these conditions.

Racing - Service

Created by Ben Grasseschi, Toko Tech Team member since 2003.

Check the [Wax Tips](#) page at [TokoUS.com](http://TokoUS.com) before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at [TokoUS.com](http://TokoUS.com).