

# WAX RECOMMENDATION

# TOKO<sup>®</sup>

## Solitude Nordic Spring Fling

Solitude Nordic Center, Brighton, UT

Saturday, March 11

10 A.M. 7K Free technique, mass start

1 P.M. Sprint, 1.2K x 3-person relay

[www.utahnordic.com](http://www.utahnordic.com)

**Forecast/Conditions:** Overnight low of 27, temperature at start near 40, chance of new snow mixed with partially transformed snow, mostly sunny.

**Glidewax:** Apply LF Black, scrape and brush, then apply HF Red/HF Yellow mixed 1:1, scrape and brush. Finish by crayoning JetStream Red, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

**Structure:** Universal grind covered by one pass with the Red Structurite tool ( before Jetstream application) will best suit these conditions.

# Racing - Service

Check the [Wax Tips](http://TokoUS.com) page at [TokoUS.com](http://TokoUS.com) before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at [TokoUS.com](http://TokoUS.com).