

# WAX RECOMMENDATION

# TOKO<sup>®</sup>

## Bjornloppet Freestyle

Bear Valley XC, Bear Valley, CA

Saturday, March 11

10:30 A.M.

20K/10K, Freestyle

Mass start

2 laps

<http://www.bearvalleyxc.com>

**Forecast/Conditions:** Overnight low 32, temperature at start 36, high of 48. Transforming/transformed snow. Mostly sunny with light winds.

**Glidewax:** Apply LF Black, scrape and brush, then apply HF Red/HF Yellow mixed 1/1, scrape and brush. Finish by crayoning JetStream Yellow, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad and/or finish by spraying an even layer of HelX 2.0 Yellow, let dry and ski. Do not brush or polish HelX.

**Gripwax:** N/A

**Structure:** A universal warm structure covered by one pass with the Yellow Structurite tool (before JetStream application) will best suit these conditions.

Created by Ben Grasseschi, Toko Tech Team member since 2003.

Check the [Wax Tips](#) page at [TokoUS.com](http://TokoUS.com) before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at [TokoUS.com](http://TokoUS.com).

# Racing - Service