

WAX RECOMMENDATION



Biathlon Cup #3

Rendezvous Biathlon Range, West Yellowstone, MT

Sunday, February 4

11 A.M. start

20K/15K/12.5K, Skate

Individual start

www.skirunbikemt.com

Forecast/Conditions: Overnight low near 25 with a 60 percent chance of 1"-3" new snow. Sunday snow likely. Temperature at start near 30. Expect softer fresh snow conditions.

Glidewax: Apply LF Black, scrape and brush, then apply HF Red, scrape and brush. Finish by crayoning JetStream Red, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad. U14 & under, apply NF Red, scrape and brush.

Gripwax: n/a

Structure: A universal structure covered by one pass with the Red Structurite tool (before JetStream application) will best suit these conditions. If snow has significant moisture, a second pass with the Red Structurite tool could be applied.

Created by Eric Mittelsteadt, Toko Tech Team member since 1999. ericm@TokoUS.com

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream or HelX) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at TokoUS.com.

Racing - Service