

# WAX RECOMMENDATION



## Moraloppet

Vasaloppet Nordic Center, Mora, MN

Saturday, February 3

11 A.M.

20K/10K, Skate

<https://vasaloppet.us/moraloppet-ski-for-the-cause/>

**Forecast/Conditions:** There is a chance of snow Friday night and Saturday during the race. Friday night's low is expected around 1F, with race time temperature in the mid-single digits and winds 5 - 10 mph. Mostly cloudy skies and a 50 percent chance of snow.

**Glidewax:** Apply LF Blue, scrape and brush, then apply HF Blue, sprinkle on X-cold Powder, iron in together, scrape and brush. Finish by crayoning JetStream Blue, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a Thermocork.

**Gripwax:** N/A

**Structure:** A fine linear grind covered by one pass with the Blue Structurite tool before JetStream application will best suit these conditions.

Created by Mike Lundeen, Toko Tech Team member since 2004.

Check the [Wax Tips](#) page at [TokoUS.com](http://TokoUS.com) before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream or HelX) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at [TokoUS.com](http://TokoUS.com).

Racing - Service