

WAX RECOMMENDATION



Winona Forest Tourathon

Winona Forest Trails, Mannsville, NY

Saturday, February 10

8 A.M.

50K/25K/12.5K, Classical

Start based on distance

12.5K loop

<https://www.skireg.com/winona-forest-tourathon>

Forecast/Conditions: Overnight low 24, temperature at start 24, machine groomed packed powder surface. Cloudy with 25 percent chance of precipitation.

Glidewax: Apply LF Black, scrape and brush, then apply HF Red, scrape and brush. Finish by crayoning JetStream Red, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: Roughen base with 150 grit sandpaper, iron in Nordic Base Wax Green, cork smooth, let cool. Then apply 3 layers of Nordic GripWax Red, corking between layers.

Structure: A universal structure covered by one pass with the Red Structurite tool (before JetStream application) will best suit these conditions.

Racing - Service

Created by Duncan Douglas, Toko Tech Team member. douglas6xc@gmail.com

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream or HelX) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at TokoUS.com.