

WAX RECOMMENDATION



Black Mountain Freestyle

Bluffs on Black Lake, Cheboygan, MI

Saturday, March 3, 2018

10:00 A.M.

20K Freestyle

Mass Start, 4 laps, 5 Km Loop

<http://nordicskiracer.com>

Forecast/Conditions: Overnight low of 16°F with temperature at start of 22 °F. Mostly sunny with a little chance of snow during race. Conditions should be machine groomed, hard packed transformed snow.

Glidewax: Apply LF Black, scrape and brush, then apply HF Blue/HF Red mixed 1/1, scrape and brush. Finish by crayoning JetStream Red, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: NA

Structure: A universal grind covered by one pass with the Red Structurite tool before JetStream application will best suit these conditions.

Created by Nickola Baic, Toko Tech Team member since 2007. Nick@TokoUS.com

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream or HelX) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at TokoUS.com.

Racing - Service