

# WAX RECOMMENDATION



## Gunstock Zak Attack Freestyle

Gunstock Nordic Center, Gilford, NH

Saturday, January 5

10 A.M.

4.2K to 12.6K, Freestyle

Interval start

1 to 3 4.2K Laps

<http://www.gunstocknordic.com>

**Forecast/Conditions:** Overnight low of 25. Temperature at start 30, mostly cloudy, a 40 percent chance of snow. Mix of new and manmade snow, PistenBully groomed trails.

**Glidewax:** Apply LF Black, scrape and brush, then apply HF Red/Yellow mixed 1/1, scrape and brush. Finish by crayoning JetStream Yellow, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

**Gripwax:** N/A

**Structure:** A universal grind covered by one pass with the Red Structurite tool before JetStream application will best suit these conditions.

Created by Stuart Kremzner, Toko Tech Team member since 2005.

Check the [Wax Tips](#) page at [TokoUS.com](http://TokoUS.com) before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream or HelX) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at [TokoUS.com](http://TokoUS.com).

Racing - Service