

# WAX RECOMMENDATION



## 4<sup>th</sup> Annual Shoot Out at Jeremy Ranch

Jeremy Ranch Golf Course, Park City, UT

Saturday, January 12

10 A.M. first starter, Individual starts

10K Skate

4 laps on a 2.5K loop

Pre-registration only, closes at 3 P.M. Friday

[www.skireg.com/4th-annual-shoot-out-at-jeremy-ranch](http://www.skireg.com/4th-annual-shoot-out-at-jeremy-ranch)

Forecast/Conditions: Overnight low 11. Temperature at start in the low 20s and sunny. Expect mostly old and partially transformed snow.

Glidewax: Apply LF Black, scrape and brush, then apply HF Red, scrape and brush. Finish by crayoning JetStream Red, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Structure: A universal stonegrind will best suit these conditions covered by one pass with the Red Structurite tool before JetStream application.

Racing - Service

Check the [Wax Tips](http://TokoUS.com) page at [TokoUS.com](http://TokoUS.com) before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream or HelX) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at [TokoUS.com](http://TokoUS.com).