

WAX RECOMMENDATION



U.S. Biathlon Western Championships Sprint

Rendezvous Trails, West Yellowstone, MT

Saturday, January 26

11 A.M. Start

10K, 7.5K, 6K & 4.5K races

<http://www.skirunbikemt.com/biathlon.html>

Forecast/Conditions: Overnight low around 6F, temperature at start in the mid- to upper teens. Expect cold packed powder conditions.

Glidewax: Apply LF Blue, scrape and brush, then apply HF Blue, scrape and brush. Finish by crayoning JetStream Blue, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: n/a

Structure: A fine structure covered by one pass with the Blue Structurite tool (before JetStream application) will best suit these conditions.

Created by Eric Mittelsteadt, Toko Tech Team member since 1999. ericm@TokoUS.com

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream or HelX) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at TokoUS.com.

Racing - Service