

WAX RECOMMENDATION



Great Sacandaga Mini Marathon

Saratoga Biathlon Club, Hadley, NY

Saturday, February 16

Noon

30K and 15K, Freestyle technique

Wave start

Multiple laps

<http://www.saratogabiathlon.com/blog/event-schedule/>

Forecast/Conditions: Overnight low 22, temperature at start 29, fresh powder, cloudy skies, with no precipitation during the day.

Glidewax: Apply LF Black, scrape and brush, then apply HF Red/HF Yellow mixed 1/1, scrape and brush. Finish by crayoning JetStream Red, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: N/A

Structure: A universal structure covered by one pass with the Red Structurite tool (before JetStream application) will best suit these conditions.

Created by Duncan Douglas, Toko Tech Team member. douglas6xc@gmail.com

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream or HelX) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at TokoUS.com.

Racing - Service