

WAX RECOMMENDATION



New England Club Relay Championship

Craftsbury Nordic Center, Craftsbury, VT

Sunday, March 10

11 A.M. Men and Women

4 x 5K Relay; two Classic, then two Skate legs

Mass start

5K loop

www.mansfieldnordic.org

Forecast/Conditions: Saturday overnight low in the low teens.

Temperature at start in the high 20s. PistenBully packed powder, temperature later in the race rising to about 30. Windy with a 70 percent chance of snow.

Glidewax: Apply LF Black, scrape and brush, then apply HF red, scrape and brush. Finish by crayoning JetStream Red, iron hot (320F) with a layer of fiberlene under the iron, traveling slowly (60 seconds) tip to tail. Brush with a dedicated nylon polishing brush and polish with a thermopad.

Gripwax: Roughen base with 150 grit sandpaper, iron in Nordic Base Wax Green, cork smooth, let cool. Then apply 3 layers of Nordic GripWax Red, corking between layers.

Structure: A universal structure covered by one pass with the Red Structurite tool after JetStream application and before brushing will best suit these conditions.

Created by Dave Boucher, Toko Tech Team member since 1999.

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the Fluorocarbon (JetStream or HelX) and substitute the LF or NF wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the How To link at TokoUS.com.

Racing - Service