

WAX RECOMMENDATION



Crosscut Biathlon Race #1 - Sprint Race

Crosscut Mountain Sports Center, Bozeman, MT

Saturday, January 18

10 A.M.

Individual start on 3 lap course

www.crosscutmt.org/events/bridger-biathlon-race-1

Forecast/Conditions: Overnight low near 13. Saturday partly sunny with temperature at start near 20. Expect clean snow that is fairly dry and abrasive. The snow has been skiing on the cold and dry/windblown side so best to harden up base with wax that is colder than the air temperature would suggest.

Glidewax: Apply Performance Blue Hot Wax, scrape and brush, then apply High Performance Blue Hot Wax, scrape and brush. For HP Liquid Paraffin, apply Performance Blue Hot Wax, scrape and brush, then spray on HP Liquid Blue, let sit in a warm room for at least one hour (overnight is best), polish with the Polishing Brush Liquid Paraffin.

Gripwax: Roughen base with 150 grit sandpaper, iron in Nordic Base Wax Green, cork smooth, let cool. Then apply 3 layers of Nordic GripWax Red, corking between layers.

Structure: A fine structure will best suit these conditions. If skis have a super fine structure, cover with one pass using the Blue Structurite tool after scraping and brushing HP Hot Wax or before spraying HP LP.

Created by Eric Mittelsteadt, Toko Tech Team member since 1999. ericm@TokoUS.com

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the High Performance (Liquid Paraffin or Hot Wax) and substitute the Performance or Base Performance wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.

Racing - Service