

WAX RECOMMENDATION

TOKO[®]

WYSEF/ALTIUS Biathlon #2 Individual Format

Rendezvous Ski Trail, West Yellowstone, MT

Saturday, January 4

10 A.M. Start

15K & under distances (see website)

Interval start

<http://www.skirunbikemt.com/biathlon1.html>

Forecast/Conditions: Overnight low near 10F, temperature at start near 16 with possible snow. Expect cold, dry and packed clean snow, typical for West Yellowstone this time of the year.

Glidewax: Apply Performance Blue Hot Wax, scrape and brush, then apply High Performance Blue Hot Wax, scrape and brush. For HP Liquid Paraffin, apply Performance Blue Hot Wax, scrape and brush, then spray on HP Liquid Blue, let sit in a warm room for at least one hour (overnight is best), polish with the Polishing Brush Liquid Paraffin.

Gripwax: n/a

Structure: A fine to fine-universal structure will best suit these conditions. If your skis have a super fine structure, cover with one pass with the Blue Structurite tool after scraping and brushing HP Hot Wax or before spraying HP LP.

Created by Eric Mittelsteadt, Toko Tech Team member since 1999. ericm@TokoUS.com

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. The Toko Race Wax Tips offer racers precise waxing advice on how to make your skis perform optimally for a given event. For racers who don't have top end waxes, skip the High Performance (Liquid Paraffin or Hot Wax) and substitute the Performance or Base Performance wax of the same color (Yellow, Red or Blue). To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.

Racing - Service