

WAX RECOMMENDATION



NSAA Kincaid Classic

Kincaid Park, Anchorage, AK

Sunday, January 24

Noon

25K/15K/5K/3K; If you want to use your wooden skis, choose the 3K or 5K courses

Multiple courses, Classic technique

www.anchoragenordicski.com/amh-anchorage-cup-series/

Forecast/Conditions: Overnight low around 25, temperature at start near 30. Well-groomed clean snow. Partly sunny, 60 percent chance of new snow on Saturday.

Glidewax: Apply Base Performance Blue Hot Wax, scrape and brush. Spray on Base Performance Red Liquid Paraffin, let stand overnight, then polish with the Polishing Brush Liquid Paraffin. If you do not have LP spray, after scraping and brushing BP Blue Hot Wax, apply BP Red Hot Wax, scrape and brush.

Gripwax: Roughen base with 150 grit sandpaper, iron in Nordic Base Wax Green, cork smooth, let cool. Then apply 3 layers of Nordic GripWax Red, corking between layers.

Structure: A warm universal stonegrind covered by one light pass with the Red Structurite tool after scraping and brushing the final BP Hot Wax or before spraying BP Liquid will best suit these conditions.

Racing - Service

Created by Ira Edwards, Toko Tech Team member since 1995. Email ira@bluedotdist.com

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. Toko Race Wax Tips offer racers precise waxing advice on how to make skis perform optimally for a given event. If an event allows fluorinated waxes and you choose to use them, use High Performance or Performance (Liquid Paraffin or Hot Wax) of the same color (Yellow, Red or Blue), as the temperature ranges are the same. To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.