

WAX RECOMMENDATION **TOKO**[®]

IMD Freestyle Sprints

Rendezvous Trails, West Yellowstone, MT

Saturday, December 18

9 A.M. Qualification; heats to follow

1.4K Sprint Course; Freestyle technique

<https://www.bridgerskifoundation.org/events/nordic-imd>

Forecast/Conditions: Overnight low around -2F. Mostly cloudy on race day with temperature at 9A.M. near 9F. Late morning to mid-afternoon temperature in the mid- to upper teens. Expect cold dry snow.

Glidewax: Apply High Performance Blue Hot Wax, scrape and brush. Spray on High Performance Blue Liquid Paraffin, let stand overnight, then polish with the Polishing Brush Liquid Paraffin. If you do not have LP spray, start with BP Blue Hot Wax, scrape and brush, and then apply HP Blue Hot Wax, scrape and brush.

Gripwax: N/A

Structure: A fine/uni or universal structure covered by one pass with the Blue Structurite tool after scraping and brushing HP Hot Wax or before spraying HP LP will best suit these conditions.

Racing - Service

Created by Eric Mittelsteadt, Toko Tech Team member since 1999. ericmittel@gmail.com

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. Toko Race Wax Tips offer racers precise waxing advice on how to make skis perform optimally for a given event. If you do not have High Performance wax, substitute Performance or Base Performance wax of the same color (Yellow, Red or Blue), as the temperature ranges are the same. All Race Wax Tips recommend ONLY fluorine-free products. Older HP or P Toko waxes (Liquid or Hot Wax) contain fluorine. New labels look very similar but all say PFC Free. To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.