

WAX RECOMMENDATION



50th Vasaloppet USA

Start and finish in downtown Mora, MN

Sunday, February 13

9 A.M. 48K/24K, Classic

Mass start on this 24K course

<https://vasaloppet.us>

Forecast/Conditions: Overnight low of -8F rising to -4F at the start. Mostly sunny and calm. Expect this course, consisting of the Thursday snowfall tilled into manmade snow, to be in excellent condition.

Glidewax: Apply High Performance Blue Hot Wax, scrape and brush. Spray on High Performance Blue Liquid Paraffin, let stand overnight, then polish with the Polishing Brush Liquid Paraffin. If you do not have LP spray, apply BP Blue Hot Wax, scrape and brush, then apply HP Blue Hot Wax, scrape and brush.

Gripwax: Roughen base with 150 grit sandpaper, iron in Nordic Base Wax Green, cork smooth, let cool. Then apply two layers of Nordic GripWax Red as a cushion in the klister zone, corking between layers, followed by additional layers of Nordic GripWax Blue, starting over the entire kick zone and pyramiding as normal to the klister zone.

Structure: A fine or universal structure covered by one pass with the Blue Structurite tool after scraping and brushing HP Hot Wax or before spraying HP LP will best suit these conditions.

Racing - Service

Created by Gerald Slater, Toko Tech Team member since 2006. grslater@comcast.net

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. Toko Race Wax Tips offer racers precise waxing advice on how to make skis perform optimally for a given event. If you do not have High Performance wax, substitute Performance or Base Performance wax of the same color (Yellow, Red or Blue), as the temperature ranges are the same. All Race Wax Tips recommend ONLY fluorine-free products. Older HP or P Toko waxes (Liquid or Hot Wax) contain fluorine. New labels look very similar but all say PFC Free. To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.