

WAX RECOMMENDATION



TOUR DE STOWE

Trapp Family Lodge, Stowe, VT - Sunday, Feb 2

10 A.M., 22k/14k/5k, Classic

Self start – one or two laps. **Non-competitive tour**

<https://nensa.net/event/stowe-nordic-tour-de-stowe/>

Forecast/Conditions: Overnight low of -6F rising to 6F by event start. Powder snow well-packed and groomed.

Glidewax: Apply HP Blue Hot Wax, scrape and brush, spray on HP Liquid Paraffin Blue, let stand overnight, then polish with the Polishing Brush Liquid Paraffin. If you do not have LP, apply BP Blue Hot Wax, scrape and brush, then apply HP Blue Hot Wax, scrape and brush.

Gripwax: Roughen base with 150 grit sandpaper, iron in Nordic Base Wax Green, cork smooth, let cool. Then apply 2-4 layers of Nordic GripWax Blue, corking smooth between layers.

Structure: A fine structure covered by one pass with the Blue Structurite tool after scraping and brushing the final Hot Wax will best suit these conditions.

Created by Rob Bradlee, Toko Tech Team member since 2000

Racing-Service

Check the [Wax Tips](#) page at TokoUS.com before all of your races for the latest waxing information. Toko Race Wax Tips offer racers precise waxing advice on how to make skis perform optimally for a given event. If you do not have High Performance wax, substitute Performance or Base Performance wax of the same color (Yellow, Red or Blue), as the temperature ranges are the same. All Race Wax Tips recommend ONLY fluorine-free products. Older HP or P Toko waxes (Liquid or Hot Wax) contain fluorine. New labels look very similar but all say PFC Free. To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.