

# WAX RECOMMENDATION



## ADK TOUR DE SKI

**Mt. Van Hoevenberg, Lake Placid, NY - Sunday, Dec 14**

11 A.M., 5k/10k, Classic or Freestyle (your choice for non-JNQ competitors)

Mass start – 2 laps

<https://www.skireg.com/adk-tour-de-ski-mt-van-hoevenberg-lake-placid>

---

**Forecast/Conditions:** Overnight low 8F, temperature at start 17, a mixture of manmade and plenty of new fallen, dry snow. A 40 percent chance of snow during the morning continuing on through the race. Excellent early season conditions, PistenBully groomed.

**Glidewax:** Apply HP Blue Hot Wax, scrape and brush, sprinkle on [Jet Powder](#) Blue, make two passes with iron at 180c, let cool, scrape and brush using the copper brush and polish with a merino wool roller. Then quickly (1 second) spray [Jet Liquid](#) Blue tail to tip, spread and polish using a handheld Thermo Cork, and go ski.

**Gripwax:** Roughen base with 150 grit sandpaper, iron in Nordic Base Wax Green, cork smooth, let cool. Then apply 2-4 layers of Nordic GripWax Blue, corking smooth between layers.

**Structure:** A universal structure covered by one pass with the Blue Structurite tool after scraping and brushing the final Hot Wax or polishing the Jet Powder but before applying Jet Liquid will best suit these conditions.

---

*Created by Duncan Douglas, Toko Tech Team member*

***Racing-Service***

---

Check the [Wax Tips](#) page at [TokoUS.com](https://www.toko-us.com) before all of your races for the latest waxing information. Toko Race Wax Tips offer racers precise waxing advice on how to make skis perform optimally for a given event. If you do not have High Performance wax, substitute Performance or Base Performance wax of the same color (Blue, Red or Yellow), as the temperature ranges are the same. For a more economical option, omit Jet topcoats. All Race Wax Tips recommend ONLY fluorine-free products. To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.