

WAX RECOMMENDATION



WYSEF/ALTIUS SHORT INDIVIDUAL BIATHLON

Rendezvous Ski Trails, West Yellowstone, MT – Sunday, Feb 15

9 A.M. Zero, 10 A.M. Race, 12.5k/4.5k, Skate

Interval start, multiple laps

<https://www.skireg.com/wysefaltius-biathlon-feb>

Forecast/Conditions: Overnight low 19, temperature at start 25, high of 39 with snow showers expected before 11 A.M. Expect dry snow and a firm track that will hold up throughout the race.

Glidewax: Apply HP Blue Hot Wax, scrape and brush, sprinkle on [Jet Powder](#) Blue, make two passes with iron at 180c, let cool, scrape and brush using the copper brush and polish with a merino wool roller. Then quickly (1 second) spray [Jet Liquid](#) Blue tail to tip, spread and polish using a handheld Thermo Cork, and go ski.

Gripwax: N/A

Structure: A universal structure covered by one pass with the Blue Structurite tool after scraping and brushing the final Hot Wax or polishing the Jet Powder but before applying Jet Liquid will best suit these conditions.

Created by Jim Rucker, Toko Tech Team member since 2023

Racing-Service

Check the [Wax Tips](#) page at [TokoUS.com](https://www.toko.com) before all of your races for the latest waxing information. Toko Race Wax Tips offer racers precise waxing advice on how to make skis perform optimally for a given event. If you do not have High Performance wax, substitute Performance or Base Performance wax of the same color (Blue, Red or Yellow), as the temperature ranges are the same. For a more economical option, omit Jet topcoats. All Race Wax Tips recommend ONLY fluorine-free products. To see optimal application procedures for both Glidewax and Gripwax, go to the [How To](#) link at TokoUS.com.